

(12) **UK Patent Application** (19) **GB** (11) **2 265 612** (13) **A**

(43) Date of A publication 06.10.1993

(21) Application No **9304305.7**

(22) Date of filing **03.03.1993**

(30) Priority data

(31) **921007**

(32) **30.03.1992**

(33) **IE**

(71) Applicant

**Chemifloc Technologies Limited**

**(Incorporated in Ireland)**

**Smithstown Industrial Estate, Smithstown, Shannon,  
County Clare, Ireland**

(72) Inventors

**Edward Anthony Storey**

**Bernard Hilary Lawless**

(74) Agent and/or Address for Service

**Wither & Rogers**

**4 Dyer's Buildings, Holborn, London, EC1N 2JT,  
United Kingdom**

(51) INT CL<sup>5</sup>

**C01B 33/10**

(52) UK CL (Edition L)

**C1A AB1E AB1X**

**U1S S1443**

(56) Documents cited

**GB 1309086 A**

(58) Field of search

**UK CL (Edition L) C1A AB1X**

**INT CL<sup>5</sup> C01B**

**Online databases: WPI; CLAIMS; JAP10**

(54) **A method for stabilising a fluosilicic acid solution**

(57) A method for stabilising a fluosilicic acid solution containing a trace of sulphate during storing and transportation in a stainless steel container, the method comprises adding food grade oxidising agent, eg hydrogen peroxide, to the solution to the amount of 0.02% to 0.07% by weight of the solution. In the example described, the solution contains 85% water, 14% fluosilicic acid and approximately 0.2% sulphate.

GB 2 265 612 A

A METHOD FOR STABILISING A FLUOSILICIC  
ACID SOLUTION

---

The present invention relates to a method for stabilising a fluosilicic acid solution containing a trace of sulphate during storing in a metal container, and in particular, during storage in a stainless steel container. The invention also relates to a stabilised fluosilicic acid solution as well as a container containing the stabilised fluosilicic acid solution.

Fluosilicic acid is used as a source of fluoride in the fluoridation of local authority water supply schemes for human consumption. In general, the fluosilicic acid is added to the water supply in relatively low proportions as the water is being metered from a reservoir. The fluosilicic acid is normally supplied in a water solution containing approximately 14% by weight of fluosilicic acid and is normally transported to the site in a stainless steel container and may be stored on site in a stainless steel container. In general, fluosilicic acid contains trace impurities, one of which is a sulphate. When stored in a metal container, in particular, a stainless steel container, the fluosilicic acid reacts with the metal of the stainless steel container in a reducing reaction, which reduces the sulphate in the fluosilicic acid to sulphide and hydrogen sulphide is formed. This results in a unpleasant "rotten egg" type odour. While the reduction of the sulphate to

sulphide does not affect the fluosilicic acid solution, it is nonetheless objectionable.

There is therefore a need for a method for stabilising a fluosilicic acid solution containing a trace of sulphate during storing and/or transportation in a metal container. There is also a need for a stabilised fluosilicic acid solution and a metal container containing the stabilised fluosilicic acid solution.

10 The present invention is directed towards providing such a method, a stabilised fluosilicic acid solution and a metal container containing the fluosilicic acid solution.

According to the invention, there is provided a method for stabilising a fluosilicic acid solution containing a trace of sulphate when stored in a metal container, the solution comprising up to 30% by weight of fluosilicic acid and up to 1% by weight of sulphate, the method comprising the step of adding a food grade oxidising agent to the solution, the oxidising agent constituting in the range of 0.02% to 0.07% by weight of the solution.

In one embodiment of the invention the oxidising agent constitutes in the range of 0.03% by weight to 0.05% by weight of the solution. Preferably, the oxidising agent constitutes approximately 0.04% by weight of the  
5 solution.

In another embodiment of the invention the oxidising agent is hydrogen peroxide.

In a further embodiment of the invention the fluosilicic acid solution is stored in a stainless  
10 steel container.

In one aspect of the invention the fluosilicic acid constitutes up to 20% by weight of the solution.

In another aspect of the invention the fluosilicic acid constitutes up to approximately 14% by weight of  
15 the solution.

In another aspect of the invention the sulphate constitutes up to 0.5% by weight of the solution. In a further aspect of the invention the sulphate constitutes up to approximately 0.2% by weight of the  
20 solution.

In a still further embodiment of the invention the solution is a fluosilicic acid/water solution.

Additionally, the invention provides a stabilised fluosilicic acid solution comprising up to 30% by weight of fluosilicic acid and up to 1% by weight of sulphate and a food grade oxidising agent, the food grade oxidising agent constituting in the range of 0.02% to 0.07% by weight of the solution.

In one embodiment of the invention the oxidising agent constitutes in the range of 0.03% by weight to 0.05% by weight of the solution. Preferably, the oxidising agent constitutes approximately 0.04% by weight of the solution.

In another embodiment of the invention the oxidising agent is hydrogen peroxide.

In one aspect of the invention the fluosilicic acid solution is stored in a stainless steel container.

In another aspect of the invention the fluosilicic acid constitutes up to 20% by weight of the solution.

In a still further aspect of the invention the fluosilicic acid constitutes up to approximately 14%

by weight of the solution.

In another aspect of the invention the sulphate constitutes up to 0.5% by weight of the solution.

In another aspect of the invention the sulphate  
5 constitutes up to approximately 0.2% by weight of the solution.

In a still further aspect of the invention the solution is a fluosilicic acid/water solution.

Further the invention a metal container containing the  
10 stabilised solution of fluosilicic acid according to the invention.

In one embodiment of the invention the metal container is of stainless steel.

The invention will be more clearly understood from the  
15 following description of a preferred embodiment thereof, given by way of the following non-limiting example.

A fluosilicic acid solution comprises the following constituents in the proportions by weight of the  
20 solution set out below:

water	85 %
fluosilicic acid	14 %
sulphate	0.2%
other impurities	0.8%

5 The fluosilicic acid solution is for use in the  
fluoridization of a local authority water supply  
scheme for human consumption. The fluosilicic acid is  
to be transported by road in a tanker having a  
stainless steel tank within which the fluosilicic acid  
10 is to be transported. The fluosilicic acid may also  
be stored prior to transportation and on the local  
authority water supply site in a stainless steel  
container. The fluosilicic acid solution is  
stabilised to prevent the sulphate being reduced as a  
15 result of reacting with the stainless steel container.  
Stabilisation is achieved by adding a food grade  
oxidising agent to the fluosilicic acid solution. In  
this embodiment of the invention, the oxidising agent  
is food grade hydrogen peroxide and constitutes  
20 approximately 0.04% by weight of the fluosilicic acid  
solution. The hydrogen peroxide may be added to the  
solution prior to being delivered into the stainless  
steel container, simultaneously as the fluosilicic  
acid solution is being delivered into the container,  
25 or just as the fluosilicic acid solution has been  
delivered into the container.

It has been found that the presence of the hydrogen peroxide in the fluosilicic acid solution prevents reduction of the sulphate in the fluosilicic acid solution forming hydrogen sulphide. The above  
5 described fluosilicic acid solution stabilised with hydrogen peroxide failed to exhibit any trace of hydrogen sulphide after being stored in a stainless steel tank for five days.

Why these new and surprising results are achieved are  
10 not fully understood, however, the following is advanced by way of explanation. It has been found that solutions of fluosilicic acid when stored in stainless steel containers produce blackening of the stainless steel in the containers, along with the  
15 production of a greenish-black colour of the fluosilicic acid solution, and the evolution of hydrogen sulphide. It is believed that the blackening of the stainless steel is caused by the fluosilicic acid attacking the stainless steel in a reducing  
20 reaction. In the process of the reducing reaction, sulphate present as an impurity in the fluosilicic acid is reduced to sulphide. The sulphide reacts with the iron in the stainless steel to form a black insoluble ferrous sulphide layer. It is believed that  
25 the greenish-black colour of the fluosilicic acid solution arises from solubilisation of non-ferrous



metals in the stainless steel.

Tests have been carried out on metal coupons of various stainless steels, namely, stainless steel 304, stainless steel 316 and stainless steel 316L, which  
5 have been immersed in respective beakers of fluosilicic acid solutions. In the tests it has been demonstrated that the coupons immersed in the fluosilicic acid solutions develop a black coating after a period of two to six hours in the solutions,  
10 and additionally, the fluosilicic acid solution turns green. On agitation of the beaker, specks of the black coating dispersed in the fluosilicic acid solution give a greenish-black appearance to the fluosilicic acid solution. The solution also emits a  
15 strong smell of hydrogen sulphide. When similar tests were carried out with stainless steel coupons with similar grades of stainless steel immersed in fluosilicic acid solutions stabilised with food grade hydrogen peroxide, wherein the food grade hydrogen  
20 peroxide constituted in the range of 0.02% to 0.07% of the solution, no blackening of the stainless steel coupons occurred. In fact, the surfaces of the stainless steel coupons remained shining and bright. Additionally, the stabilised fluosilicic acid solution  
25 remained colourless and there was no smell of hydrogen sulphide, indicating the absence of hydrogen sulphide

in the solution. The stainless steel coupons were left in the respective fluosilicic acid solutions for ten days, and after ten days, no blackening of the stainless steel coupons was detected, the colour of  
5 the fluosilicic acid solution remained unchanged, and there was no indication of the presence of hydrogen sulphide.

While the food grade oxidising agent has been described as being food grade hydrogen peroxide, it is  
10 envisaged that other suitable food grade oxidising agents may be used.

CLAIMS

1. A method for stabilising a fluosilicic acid solution containing a trace of sulphate when stored in a metal container, the solution comprising up to 30%  
5 by weight of fluosilicic acid and up to 1% by weight of sulphate, the method comprising the step of adding a food grade oxidising agent to the solution, the oxidising agent constituting in the range of 0.02% to 0.07% by weight of the solution.
- 10 2. A method as claimed in Claim 1 in which the oxidising agent constitutes in the range of 0.03% by weight to 0.05% by weight of the solution.
3. A method as claimed in Claim 2 in which the oxidising agent constitutes approximately 0.04% by  
15 weight of the solution.
4. A method as claimed in any preceding claim in which the oxidising agent is hydrogen peroxide.
5. A method as claimed in any preceding claim in which the fluosilicic acid solution is stored in a  
20 stainless steel container.
6. A method as claimed in any preceding claim in which the fluosilicic acid constitutes up to 20% by

weight of the solution.

7. A method as claimed in any preceding claim in which the fluosilicic acid constitutes up to approximately 14% by weight of the solution.
- 5 8. A method as claimed in any preceding claim in which the sulphate constitutes up to 0.5% by weight of the solution.
9. A method as claimed in any preceding claim in which the sulphate constitutes up to approximately  
10 0.2% by weight of the solution.
10. A method as claimed in any preceding claim in which the solution is a fluosilicic acid/water solution.
11. A method for stabilising a fluosilicic acid  
15 solution containing a trace of sulphate when stored in a metal container, the method being substantially as described herein with reference to the example.
12. A stabilised fluosilicic acid solution comprising up to 30% by weight of fluosilicic acid and up to 1%  
20 by weight of sulphate and a food grade oxidising agent, the food grade oxidising agent constituting in

the range of 0.02% to 0.07% by weight of the solution.

13. A stabilised fluosilicic acid solution as claimed  
in Claim 12 in which the oxidising agent constitutes  
in the range of 0.03% by weight to 0.05% by weight of  
5 the solution.

14. A stabilised fluosilicic acid solution as claimed  
in Claim 13 in which the oxidising agent constitutes  
approximately 0.04% by weight of the solution.

15. A stabilised fluosilicic acid solution as claimed  
10 in any of Claims 12 to 14 in which the oxidising agent  
is hydrogen peroxide.

16. A stabilised fluosilicic acid solution as claimed  
in any of Claims 12 to 15 in which the fluosilicic  
acid solution is stored in a stainless steel  
15 container.

17. A stabilised fluosilicic acid solution as claimed  
in any of Claims 12 to 16 in which the fluosilicic  
acid constitutes up to 20% by weight of the solution.

18. A stabilised fluosilicic acid solution as claimed  
20 in any of Claims 12 to 17 in which the fluosilicic  
acid constitutes up to approximately 14% by weight of

the solution.

19. A stabilised fluosilicic acid solution as claimed in any of Claims 12 to 18 in which the sulphate constitutes up to 0.5% by weight of the solution.

5 20. A stabilised fluosilicic acid solution as claimed in any of Claims 12 to 19 in which the sulphate constitutes up to approximately 0.2% by weight of the solution.

10 21. A stabilised fluosilicic acid solution as claimed in any of Claims 12 to 20 in which the solution is a fluosilicic acid/water solution.

22. A stabilised fluosilicic acid solution substantially as described herein with reference to the example.

15 23. A metal container containing the stabilised solution of fluosilicic acid of any of Claims 12 to 22.

24. A metal container as claimed in Claim 23 in which the metal container is of stainless steel.

**Patents Act 1977**  
**Examiner's report to the Comptroller under**  
**Section 17 (The Search Report)**

-1k-  
Application number

GB 9304305.7

**Relevant Technical fields**

(i) UK CI (Edition L ) CIA (ABIX)

(ii) Int CI (Edition 5 ) C01B

**Search Examiner**

C A CLARKE

**Databases (see over)**

(i) UK Patent Office

(ii) ONLINE DATABASES: WPI; CLAIMS; JAPIO

**Date of Search**

26 MARCH 1993

**Documents considered relevant following a search in respect of claims**

Category (see over)	Identity of document and relevant passages	Relevant to claim(s)
X	GB 1309086 - (FISONS)	1,4,10 AND 15 AT LEAST

Category	Identity of document and relevant passages	Relevant to claim(s)

### Categories of documents

**X:** Document indicating lack of novelty or of inventive step.

**Y:** Document indicating lack of inventive step if combined with one or more other documents of the same category.

**A:** Document indicating technological background and/or state of the art.

**P:** Document published on or after the declared priority date but before the filing date of the present application.

**E:** Patent document published on or after, but with priority date earlier than, the filing date of the present application.

**&:** Member of the same patent family, corresponding document.

**Databases:** The UK Patent Office database comprises classified collections of GB, EP, WO and US patent specifications as outlined periodically in the Official Journal (Patents). The on-line databases considered for search are also listed periodically in the Official Journal (Patents).